

Mitrovich p.i. Luigi & C.snc
Lubrificanti dal 1949
Sede e domicilio fiscale:
Viale Milano 53 Vicenza 36100
tel e fax : 0444- 557401
Deposito: Via E. Fermi 41/43
Costabissara (VI)36030
tel e fax : 0444- 557401
mitrovich@mitrovich.info
http://www.mitrovich.info

Waxrex 1280

Semi-Refined Paraffin Wax

Product Description

Waxrex 1280 is a lower-range melting point semi-refined paraffin wax. It is derived from petroleum via a carefully controlled refining process to provide low colour and low oil content. Waxrex 1280 meets the requirements for many industrial wax applications and also meets the requirements of RAL for candle manufacture. Waxrex 1280 is a translucent crystalline material in the solid state and is water-white in colour and low in viscosity when molten. It is composed mainly of normal, straight chain paraffin hydrocarbons, which impart properties of water repellency and resistance to most acids and alkalis.

Waxrex 1280 contains an oxidation inhibitor to enhance the natural resistance to oxidation.

ExxonMobil waxes are produced and controlled according to the ExxonMobil Product Quality Management System, EN ISO 9000 or equivalent standards.

Applications (*)

Waxrex 1280 is typically used as a component in the manufacture of candles.

(*) Applications are subject to applicable Laws and Regulations in each country

Properties and Specifications

Waxrex 1280 meets the requirements of RAL-GZ 041 for candle manufacture.

Typical values may vary within modest ranges and specifications may be subject to change.

| Property | Method | Typical | Specification | |
|---|------------|---------|---------------|------|
| | | | MIN | MAX |
| Melting Point, °C | ASTM D87 | - | 52.0 | 56.0 |
| Oil Content, wt % | ASTM D721 | - | - | 1.5 |
| Colour, Saybolt | ASTM D6045 | - | +25 | - |
| Odour, cold | ASTM D1833 | - | - | 1 |
| Penetration @ 25°C , needle, 0.1mm | ASTM D1321 | - | 12 | 23 |
| Kinematic Viscosity @ 100°C, mm ² /s (cSt) | ASTM D445 | 3.3 | - | - |
| Density, @ 85°C , kg/m ³ | ASTM D1298 | 760 | - | - |
| Density, @ 15°C , kg/m ³ [^] | ASTM D1298 | 810 | - | - |
| Flash Point COC, °C (°F) | ASTM D92 | - | 204 (399) | - |

[^] Density is based on testing liquid wax and calculating the density as a liquid at 15°C for accounting purposes.

Mitrovich p.i. Luigi & C.snc
Lubrificanti dal 1949
Sede e domicilio fiscale:
Viale Milano 53 Vicenza 36100
tel e fax : 0444- 557401
Deposito: Via E. Fermi 41/43
Costabissara (VI)36030
tel e fax : 0444- 557401

Health and Safety

<http://www.mitrovich.info>

Detailed health and safety information for this product is provided in the Material Safety Data Sheet (MSDS), available upon request through your local sales representative or from www.ExxonMobil.com

Storage and Handling

Recommended practices for safe and efficient storage and handling of bulk waxes in liquid form can be found in a separate bulletin, "Storage and Handling of Liquid Waxes".

Further Information

ExxonMobil supplies a full range of waxes, wax emulsions, white oils, process oils, bitumen and a full range of lubricants, fuels and chemical products worldwide. Please contact your local ExxonMobil representative, or contact us at www.ExxonMobil.com, for more information on other products.

ExxonMobil Lubricants & Specialties

All products may not be available locally. For more information, contact your local sales office or visit www.exxonmobil.com.

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil affiliate entities. Due to continual product research and development, the information contained herein is subject to change without notification. Typical Properties may vary slightly.

© 2001 Exxon Mobil Corporation. All rights reserved.